

Pigmofix M Fein

8106

Solvent-based matt paste for pigmented ADLER 2C PUR furniture paints for use in industry and trade

PRODUCT DESCRIPTION


Product numbers

81060000210

General

Solvent-based matt paste for reducing the degree of gloss in pigmented 2C PUR furniture paints. Stand-out features of this product include very good scratch resistance and a uniform matt finish across the entire coating system.

Application area



Matting component for solvent-based, pigmented coatings for furniture and interior finishing.

PROCESSING

Processing instructions



- Please stir and shake the product well before use (1 minute shaker).
- Carefully stir the Pigmofix M Fein (8106) into the unhardened and undiluted paint/varnish; then stir in the hardener and the required quantity of thinner.
- Mixed paints and stains must be processed as specified in the corresponding technical data sheet.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.

Quantity to be added



Max. 15 % by weight of the paint.

Example: Reduction of shine in Pigmopur G50 (2406)

For: Pigmopur G50 (2406)	degree of gloss achieved (85 ° angle)
0 %	G50
5 %	approx. G30
10 %	approx. G10

Drying times

(at 23 °C and 50 % rel. humidity)

The drying behaviour of the coating system is not affected by the addition of Pigmofix M Fein (8106).

Cleaning the working equipment

With DD-Verdüner 8519 (8519) or Waschverdünner (8501) immediately after use.



8519



8501

ORDERING INFORMATION**Size of trading unit**

600 g, 900 g, 3 kg

FURTHER DETAILS**Durability / storage**

Min. 1 year(s) in the original sealed containers.



Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Safety information

The product is only suitable for the industrial and professional use.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.
