

Nitro-Spraylack

1612

Touch-up spray coating for coated furniture surfaces for professional and industrial use

PRODUCT DESCRIPTION

General

Rapid-drying touch-up spray coating based on nitrocellulose for coated furniture surfaces. The product is characterised by very rapid drying and good flow. Spray application without lap marks.

Special properties and standards



- **ÖNORM A 1605-12 (furniture surfaces)**
Resistance to chemical reactions: 1-C

Application area



Small-scale touch-up work in furniture and interior finishing.

For touching-up assembly scratches

To touch-up damage


PROCESSING

Processing instructions



- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- Shake can vigorously for 2 minutes before use. Mixing ball must be audible. Shake occasionally during use.
- Hold the can upright and spray evenly from a distance of approx. 20 - 30 cm at room temperature, not applying too heavily.
- To assess colour consistency, grain enhancement and compatibility, a spray test must always be carried out in an inconspicuous area.
- If necessary, apply a second coat after 3 to 6 minutes; several coats are preferable to one thick coat.
- After use, turn the can upside down and spray through the nozzle until only gas comes out, to prevent the valve from sticking.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.

Application technique



Application method	Spray can
Application quantity (m ² /ml) ¹⁾	6 - 8m ² / 400 ml

Drying times

(at 23 °C and 50 % rel. humidity)



Sandable and recoatable:

approx. 10 - 15 minutes

The figures given above are reference values. Drying depends on the substrate, layer thickness, temperature, air exchange, relative humidity, stacking pressure and stacking conditions.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

SUBSTRATE**Substrate property**

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Substrate preparation**Hardwoods:** Lightly sand with 150 - 180 grit and clean**Softwoods:** Lightly sand with 100 - 150 grit and clean**COATING SYSTEM****Product application**

1 – 2 x Nitro-Spraylack (1612)

ORDERING INFORMATION**Size of trading unit**

400 ml spray can

Colour shades / Glosslevels

Nitro-Spraylack G30 Farblos, Seidenmatt (1612077811)

Nitro-Spraylack G70 Farblos, Glänzend (1612050252)

FURTHER DETAILS**Durability / storage**

Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Safety information

Spray can is under pressure. Store in a well-ventilated place. Keep spray jet away from body. During work, do not eat, drink or smoke. Do not spray against flames or on glowing objects. Even after use do not open it violently or burn it.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.