

Vivido Allwetterlack

4502

Clear **synthetic resin coating for wood for interior and exterior use** for DIY and professional use

PRODUCT DESCRIPTION

General

Solvent-based, clear synthetic resin top coating for wood for interior and exterior use with good weather resistance. The product is characterised by rapid drying, high filling power, optimal flow, good sag resistance and very good cream and grease resistance.
Yacht varnish quality.

Application area



For the coating of wood for exterior and interior use, e.g. wooden doors, garden furniture, table tops, beer tables and gates.

Protective coating for opaque KH coatings or wood stains.

The product is not suitable for interior surfaces of furniture and cabinets due to possible odour nuisance.

PROCESSING

Processing instructions



- **Spraying is only allowed in spray booths complying with the VOC Directive.**
- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least + 5 °C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost.
- Resin flow cannot be avoided by the coating application.
- The color shade, compatibility and adhesion to the substrate must be checked by creating sample panels.
- Water-soluble wood extracts can be leached particularly by driving rain. This can be minimized by an all-over coating and additional sealing of the end grains.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please follow our **ARL 500 - Working guideline for coating non-dimensionally stable and limited dimensionally stable construction elements – General part.**
- Please follow our **ARL 505 - Working guideline for alkyd resin coatings/-glazes and oils.**

Application technique

0-5% 7231



20% 8014



	Cup gun	Brushing	Rolling
Spraying nozzle Ø (mm)	1,8 - 2,0	-	
Spraying pressure (bar)	3 - 4	-	
Diluent	KH-Spritzverdünner 8014 (8014)	-	Adlerol-Terpentinölersatz (7231)
Diluent amount added (%)	20	-	0 - 5
Applied quantity per application (ml/m²)	80 - 100	60 - 80	

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

For good thorough drying, the recommended application quantities must be adhered to. Excessive layer thicknesses lead to a considerable drying delay!

Drying times

(at 23 °C and 50 % rel. humidity)



Recoat after	approx. 12 hour(s)
--------------	--------------------

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

For good thorough drying, the recommended application quantities must be adhered to.

On types of woods rich in extracts (such as oak, iroko), drying may be delayed.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

Cleaning the working equipment

7231



7231

With Adlerol-Terpentinölersatz (7231) immediately after use.

To remove dried product residues we recommend using Clean Abbeizer-Express (8313).

SUBSTRATE**Type of substrate**

Softwoods and hardwoods as well as plywood materials, which are suitable for the exterior, such as, for example, solid wooden boards, glued laminated timber (GLT or Glulam) and solid structural timber (SST).

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.

Please observe the additional documents:

- ÖNORM B 3430-1
- ÖNORM B 2230-1
- DIN 18363
- Current BFS information sheets

Wood moisture	Hardwoods: $12 \pm 2 \%$ Softwoods: $15 \pm 2 \%$
Substrate preparation	Wood and wood-based materials: For optimal durability we recommend to sand smooth wooden surfaces with grain size 80 – 120 in the direction of the fibre, clean thoroughly and remove wood extractives such as, for example, resins and resin pockets. Round off any sharp edges. Clean resin-rich woods and exotic woods with drying retardants with Nitro-Verdünner 8017 (8017). Wood sanding: Grit size 120 Old coatings: Sand and/or leach intact old coating. Remove old coatings that cannot be recoated. The compatibility of the coating must be checked on intact old coatings. Treat algae, green deposits or mould in outdoor areas with Aviva Fungisan (8308).
COATING SYSTEM	
General	The following coating systems are exemplary.
Impregnation	Wood and wood-based materials in outdoors areas If necessary, impregnate outdoors once with Pullex Imprägnier-Grund (4436) (applies to timbers of durability class 3-5 according to EN 350) to protect against blue stain, fungal decay and insect infestation. Intermediate drying: approx. 12 hour(s) Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use. Please follow our ARL 056 - Working guideline for the use of wood preservatives.
Primer coat	1 x Vivido Allwetterlack (4502) Intermediate drying: approx. 12 hour(s)
Intermediate sanding 	Grit size 240 – 280 Remove sanding dust.
Finishing coat	1 x Vivido Allwetterlack (4502)
MAINTENANCE	
Care	The durability depends on several factors: these include particularly the type of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Vivido Allwetterlack (4502). Shorter renovation intervals must be expected for colourless exterior coatings. Increased maintenance is recommended. Damage should be repaired as quickly as possible to prevent greying. On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected.

Maintenance	Please follow our ARL 504 - Working guideline for coating non-dimensionally stable and limited dimensionally stable construction elements - Maintenance and Repair.
ORDERING INFORMATION	
Size of trading unit	375 ml, 750 ml, 2.5l
Colour shades / Glosslevels	Standard colour(s): Farblos, Glänzend (4502050252) Farblos, Matt (4502050253) Attention: Slightly yellowish inherent colour.
Supplementary products	Adlerol-Verdünner 7231 (7231) Aviva Fungisan (8308) KH-Spritzverdünner 8014 (8014) Nitro-Verdünner 8017 (8017) Pullex Imprägnier-Grund (4436) Please refer to the corresponding technical data sheets of the products.
FURTHER DETAILS	
Durability / storage 	Min. 5 year(s) in the original sealed containers. Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C). We recommend to transfer the contents of open containers to smaller ones in order to prevent gelling / skin formation. Close opened containers well and use up the content as soon as possible.
Technical specifications	VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Vivido Allwetterlack (Cat A/e): 400 g/l. Vivido Allwetterlack contains a maximum of 390 g/l VOC.
Giscode	BSL20
Declaration of ingredients according to VdL-RL 01	alkyd resins / aliphatic compounds / surface additive / glycol ether / wetting agent / drying agents (siccatives) / light stabilisers / anti-skin agent Contains phthalic anhydride. May cause allergic reactions. Information for allergy sufferers available at Tel. +43 5242 6922-713.
Safety information 	When using cloths that have been soaked with oxidative drying products, there is a risk of spontaneous combustion! Spread soaked cloths out and let them dry; it is necessary to store them in sealed metal containers or under water. Using the product in spraying booths, which are contaminated with nitrocellulose-containing spray dust, is prohibited owing to the risk of self-ignition! The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2). When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust. In case of hardwood (especially for Beech, Oak) a dust filter P3 is recommended. Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com .